



TYPICAL PROPERTIES	TEST STANDARD	UNITS S.I.	4145	4155	4165	4175	4180	4190	4139D	4149D
DENSITY	ISO 1183	kg/m ³	960	960	960	960	960	950	950	940
HARDNESS (5 SEC DELAY)										
Extruded sample	ISO 868	Shore A	45A	53A	63A	72A	79A	86A	39D	47D
Injection molded sample		or D	48A	56A	65A	75A	83A	90A	40D	51D
TENSILE PROPERTIES										
Flow direction										
Tensile strength at break	ISO 37	MPa	3.1	4.3	5.8	7.2	9.0	13.6	18.0	21.6
Modulus at 100% elongation		MPa	2.6	3.1	4.2	5.3	6.8	10.2	13.3	18.0
Elongation at break		%	180	240	280	300	330	380	420	420
Cross flow direction										
Tensile strength at break	ISO 37	MPa	4.3	5.2	6.8	8.5	10.2	14.5	19.0	23.1
Modulus at 100% elongation		MPa	1.3	2.0	2.5	3.3	4.5	6.7	8.9	13.0
Elongation at break		%	550	550	570	590	620	650	700	740
TEAR STRENGTH										
Cross flow direction	ISO 34B	kN/m	20	22	29	39	48	71	97	140
Unnicked angle										
COMPRESSION SET										
22 hrs @ 23°C	ISO 815	%	11	14	17	22	26	36	46	55
22 hrs @ 70°C		%	26	26	27	31	40	48	56	64
70 hrs @ 125°C		%	35	37	40	45	58	72	80	85
HOT AIR AGING										
Cross flow direction										
168 hrs @ 150°C	ISO 188	pts	0	2	2	3	2	3	2	2
Change in hardness		%	-5	-9	-11	-9	-10	-8	-15	-15
Change in tensile strength at break		%	-3	-2	0	3	5	10	15	15
Change in modulus at 100% elongation		%	6	-6	-11	-16	-15	-17	-20	-20
Change in elongation at break		%								
1000 hrs @ 135°C	ISO 188	pts	2	2	2	2	3	3	2	2
Change in hardness		%	-2	-5	-9	-2	-9	-11	-15	-8
Change in tensile strength at break		%	0	2	4	5	10	15	20	25
Change in modulus at 100% elongation		%	13	1	-8	-5	-15	-16	-20	-20
Change in elongation at break		%								
VOLUME SWELL										
70 hrs @ 125°C in IRM 903 oil	ISO 1817	%	110	85	83	78	64	54	47	38
APPARENT SHEAR VISCOSITY	ISO 11443									
@ 206 1/s, 200°C	Capillary	Pa.s	320	320	340	340	340	340	370	440

FEATURES

- Excellent chemical and abrasion resistance
- Fully cross-linked
- Low tension and compression set
- Low oil swell
- Excellent flex-fatigue resistance
- Available from 45 Shore A to 50 Shore D, in black and natural
- Versatile, can be processed by injection molding, extrusion, or blow molding

TRANSPORTATION SEGMENT

- Interior
- Under the Hood

Revised April 2018

AMERICAS

505 Central Avenue
Pawtucket, RI 02861 USA
401-725-8000 | 800-556-3862

EUROPE

Mijnweg 1
6167AC Geleen, Netherlands
31(0) 46 7020950

ASIA

41 Shipyard Road
Singapore 028134
(011) 65-6265-2544



tpe@teknorapex.com | www.teknorapex.com

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in any medical or food contact application without the prior written acknowledgment of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries. Data contained in this bulletin supercedes all previous versions. © Copyright 2018 Teknor Apex Company. All rights reserved.