



TYPICAL PROPERTIES	TEST STANDARD	UNITS S.I.	ME-2655B	ME-2665B	ME-2675B	ME-2685B
DENSITY	ISO 1183	kg/m ³	940	940	940	940
HARDNESS (5 SEC DELAY) Injection molded sample	ISO 868	Shore A or D	57A	62A	74A	82A
TENSILE PROPERTIES						
Flow direction						
Tensile strength at break	ISO 37	MPa	7.80	7.90	9.20	11.3
Modulus at 100% elongation		MPa	1.94	1.89	2.79	4.40
Elongation at break		%	770	770	730	680
Cross flow direction						
Tensile strength at break	ISO 37	MPa	10.5	9.80	10.5	12.7
Modulus at 100% elongation		MPa	1.56	1.60	2.55	3.70
Elongation at break		%	880	890	790	770
TEAR STRENGTH						
Cross flow direction	ISO 34B					
Unnicked angle		kN/m	23	26	33	41
COMPRESSION SET						
22 hrs @ 23°C	ISO 815	%	17	23	23	32
22 hrs @ 70°C		%	36	35	45	50
70 hrs @ 90°C		%	61	56	69	68
HOT AIR AGING						
Cross flow direction						
168hrs @ 125°C	ISO 188	pts	2	4	2	2
Change in hardness		%	5.4	3.1	-7.0	-7.1
Change in tensile strength at break		%	-	11	-	-
Change in modulus at 100% elongation		%	1.4	5.3	-1.6	-3.5
1000 hrs @ 110°C	ISO 188	pts	1.3	3.4	1.9	1.7
Change in hardness		%	8.7	0	-2	-3.1
Change in tensile strength at break		%	-	13	-	-
Change in modulus at 100% elongation		%	3	3.2	0.50	1.0
APPARENT SHEAR VISCOSITY @ 206 1/s, 200°C	ISO 11443 Capillary	Pa.s	139	129	137	140

FEATURES

- High flow properties for excellent moldability
- Low density material yielding lighter weight parts
- Class A surface appearance
- Adhesion to glass with use of primer
- Excellent UV resistance
- Good elastic performance
- Available from 55 Shore A to 40 Shore D, in black only

TRANSPORTATION SEGMENTS

- Sealing Systems
- Under the Hood

Revised April 2018

AMERICAS

 505 Central Avenue
 Pawtucket, RI 02861 USA
 401-725-8000 | 800-556-3862

EUROPE

 Mijnweg 1
 6167AC Geleen, Netherlands
 31(0) 46 7020950

ASIA

 41 Shipyard Road
 Singapore 028134
 (011) 65-6265-2544

tpe@teknorapex.com | www.teknorapex.com

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in any medical or food contact application without the prior written acknowledgment of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries. Data contained in this bulletin supercedes all previous versions. © Copyright 2018 Teknor Apex Company. All rights reserved.