


# HIVAL<sup>®</sup> Polymers

Connecting you with a network of  
thermoplastic resin SOLUTIONS

**For availability and orders:**

Toll Free (U.S.): 833.44.NEXEO | 833.446.3936 | [nexeoplastics.com](http://nexeoplastics.com)



**We Carry a Full Portfolio of  
HIVAL® Polymer Products  
for all Your Applications**

Multiple grades  
of polypropylene,  
polyethylene,  
polystyrene and ABS

Property-driven materials  
including clarified,  
low water carryover,  
nucleated and anti-stat

Readily available for  
blow molding, extrusion,  
injection molding and  
rotational molding

## POLYETHYLENE

GRADE		MELT INDEX	DENSITY	ADDITIVES*	FDA	APPLICATIONS
		g/10 min	g/cm³			
HDPE	PE HD 506060	8	0.965		Y	Injection, Crate
HDPE	PE HD 507051	6.5	0.953		Y	Injection, Pail
HDPE	PE HD 511051	12	0.951		Y	Injection
HDPE	PE HD 521054	20	0.954		Y	Injection
HDPE	PE HD 534050	33	0.952		Y	Injection
HDPE	PE HDBM 500354	0.35	0.954		Y	Blow Molding, Phillips Process
HDPE	PE HDBM 500354 AS	0.35	0.954	Anti-Stat	Y	Blow Molding, Phillips Process
HDPE	PE HDBM 500354U	0.3	0.955		Y	Blow Molding, Unipol Process
HDPE	PE HDBM 500860	0.8	0.960		Y	Blow Molding, Sheet, Dairy
HDPE	PE HDBM 5000950	10 HLMI	0.950		Y	HLMI, Sheet and Large Part, Phillips Process
HDPE	PE HDBM 5000950U	10 HLMI	0.950		Y	HLMI, Sheet and Large Part, Unipol Process
HDPE	PE HDBM 5000951 HMW	10 HLMI	0.951		Y	HMW Film Grade
LDPE	PE LD 300218	0.25	0.918	Barefoot or with Slip and AB packages	Y	Heavy Duty Blown Film
LDPE	PE LD 300721	0.7	0.921	Barefoot or with Slip and AB packages	Y	Heavy Duty Blown Film
LDPE	PE LD FL19 095	10	0.919		Y	Blow and Injection Molding
LDPE	PE LD FL20 020	2	0.920	Tubular, Barefoot	Y	Liner, Blown and Cast Film
LDPE	PE LD FL20 020 AC	2	0.920	Autoclave, Barefoot	Y	Clarity, Blown and Cast Film
LDPE	PE LD FL20 020 AC MM	2	0.929	Autoclave, Slip and Antiblock	Y	Clarity, Blown and Cast Film
LDPE	PE LD FL20 020 AC OH	2	0.920	Autoclave, Antiblock	Y	Premium Clarity, Blown and Cast Film
LDPE	PE LD FL20 020 TC	2	0.923	Tubular, Barefoot	Y	Clarity, Blown and Cast Film
LDPE	PE LD FL20 020 TC MM	2	0.920	Slip, Antiblock	Y	Film Structures
LLDPE	PE LLD 102024	20	0.924		Y	Injection
LLDPE	PE LLD 102024 PWD	20	0.924	Granular, Powder	Y	Injection / Compounding
LLDPE	PE LLD 105056 PWD	50	0.926	Granular, Powder	Y	Compounding
LLDPE	PE LLD 150025	50	0.926		Y	Injection
LLDPE	PE LLD FLLB19 020	2	0.918	Barefoot	Y	Film, Butene
LLDPE	PE LLD FLLB19 020 MM	2	0.918	Medium Slip, Medium Antiblock	Y	Blown Film, Cast Film, Butene
LLDPE	PE LLD FLLB19 028	2	0.918	Barefoot	Y	Blown Film, Butene
LLDPE	PE LLD FLLB19 0095	1	0.919	Barefoot or with Slip and AB packages	Y	Film, Butene
LLDPE	PE LLD FLLB19 0095 MM	1	0.919	Medium Slip, Medium Block	Y	Film, Butene
LLDPE	PE LLD FLLB19 0095 OH	1	0.919	No Slip / High Antiblock	Y	Film, Butene
LLDPE	PE MLLD FLLH18 010	1	0.918	Barefoot	Y	Blown Film, Extrusion, Metallocene, Hexene
LLDPE	PE MLLD FLLH18 010 MM	1	0.918	Medium Slip, Medium Antiblock	Y	Blown Film, Metallocene, Hexene
LLDPE	PE LLD FLLH18 010 OH	1	0.919	Antiblock	Y	Film Structures
LLDPE	PE MLLD FLLH18 015	1.5	0.918	Barefoot	Y	Blown Film, Metallocene, Hexene
LLDPE	PE MLLD FLLH18 015 MM	1.5	0.918	Medium Slip, Medium Antiblock	Y	Blown Film, Metallocene, Hexene
LLDPE	PE MLLD FLLH18 035	3.5	0.918		Y	Cast Film, Metallocene, Hexene
LLDPE	PE MLLD FLLH18 035 T	3.5	0.918	Medium Slip, Medium Antiblock, Tacifier	Y	Cast Film for Stretch Wrap, Metallocene, Hexene

## POLYPROPYLENE

GRADE		MELT FLOW	FLEX MOD	IZOD	ADDITIVES*	FDA	APPLICATIONS
		g/10 min	psi	ft-lb/in			
	24007	0.5	240,000	1.4		Y	Extrusion / Injection
	2403	3	240,000	0.6		Y	Extrusion / Injection, Straw Grade
	2403LW	3	240,000	0.8	LWC	Y	Extrusion / Injection, Film, Fiber, Tape
	2405	4	210,000	0.6		N	Extrusion / Injection, Straw Grade, BOPP
	2405AS	5	240,000	0.8	AS	Y	Extrusion / Injection, Straw Grade
HP	2412	12	235,000	0.5		Y	Injection, General Purpose
	2420	20	235,000	0.5		Y	Injection, General Purpose
	2420NA	20	260,000	0.4	N, AS	Y	Injection, General Purpose
	2435	35	170,000	0.5		Y	Injection, General Purpose
	2435NA	35	200,000	0.6	N, AS	Y	Injection, General Purpose
		g/10 min	psi	ft-lb/in			
	26007	0.5	170,000	NB		Y	Extrusion / Injection, Sheet, Film
	2602NB	2	150,000	NB	Barefoot	Y	Injection, Extrusion
	2604	4	180,000	1.5+	Barefoot	Y	Injection
	2604NB	4	140,000	NB	Barefoot	Y	Injection
	2604NA	4	140,000	NB	N, AS	Y	Injection
	2608HI	10	158,000	3		N	Injection, Medium Impact
CP	2610	10	232,000	1.8		Y	Injection, General Purpose
	2612NB	12	165,000	NB	N, AS	Y	Injection, High Impact
	2620	20	160,000	2		Y	Injection, General Purpose
	2620NB	20	145,000	NB		Y	Injection, High Impact / No Break
	2630NB	30	130,000	NB	N	Y	Injection, High Impact
	2635	35	155,000	1.8		Y	Injection, General Purpose
	2650	50	180,000	1.6		Y	Injection, High Flow
		g/10 min	psi	ft-lb/in			
	2502NX	2	150,000	1.1	C	Y	Extrusion / Thermoforming / Injection, Clarity
RCP	2512NX	12	160,000	1.5	C	Y	Injection, Clarity
	2535NX	35	170,000	1	C	Y	Injection, Clarity

\* LWC = Low Water Carryover

\* N = Nucleated

\* AS = Anti-Stat

\* C = Clarified NX8000

## ACRYLONITRILE BUTADIENE STYRENE

	GRADE	MELT FLOW	FLEX MOD	IZOD	FDA	APPLICATIONS
		g/10 min (230° C/3.8kg)	psi	ft-lb/in		
ABS	HG6	5.6	320,000	5.8	N	Injection
	HG9	12	359,000	4.5	N	Injection
	HGGP	10	348,000	4.4	N	Injection
	LG6	6	357,000	5.5	N	Injection

## POLYSTYRENE

	GRADE	MELT FLOW	FLEX MOD	IZOD	FDA	APPLICATIONS
		g/10 min	psi	ft-lb/in		
PS	GPPS 5102	2	425,000	0.5	Y	Injection
	GPPS 5108M	8	413,000	0.3	Y	Injection
	GPPS 5112	14	345,000	0.25	Y	Injection
	MIPS 5210	10	242,000	1.7	Y	Injection
	HIPS 5303	3	260,000	2.5	Y	Extrusion
	HIPS 5308	8	240,000	2.8	Y	Injection
	HIPS 5313	13	290,000	2	Y	Injection

\* LWC = Low Water Carryover

\* N = Nucleated

\* AS = Anti-Stat

\* C = Clarified NX8000

# Expect More.

More Resources. More Products. More Real-Time Information.

Nexeo Plastics  
1780 Hughes Landing Blvd  
Suite 1000  
The Woodlands, TX 77380 USA  
[nexeoplastics.com](http://nexeoplastics.com)

To Place Your Order:  
US & Canada: 833.446.3936  
[getplastics@nexeoplastics.com](mailto:getplastics@nexeoplastics.com)  
Mexico: +52 55 4749 1710  
[ventas@nexeoplastics.com](mailto:ventas@nexeoplastics.com)

For Technical Questions:  
US & Canada: 866.430.9666  
Mexico: +52 81 1182 5109  
[techconnect@nexeoplastics.com](mailto:techconnect@nexeoplastics.com)

All statements, information and data presented herein by Nexeo Plastics are believed to be accurate but are not to be taken as a guarantee or other representation for which Nexeo Plastics and its affiliates and subsidiaries assume legal responsibility.

NEXEO PLASTICS EXPRESSLY DISCLAIMS ANY AND ALL WARRANTIES, EITHER EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION, ANY WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARISING OUT OF ANY USE OF THE PRODUCTS OR SERVICES IDENTIFIED HEREIN OR RELIANCE ON ANY INFORMATION PROVIDED HEREIN.

All statements, information, recommendations and products must be thoroughly evaluated and verified by the end user to determine their applicability or suitability for each particular use. Typical values are indicative only and are not to be construed as being binding specifications.

\* Trademark owned by a third party

©2024 Nexeo Plastics, LLC. All Rights Reserved.

**nexeo**  
plastics

NEX-HIV-LCRD  
20240419